



ASPHALTIC DRIVEWAY SEALER –Oil Based
(PRODUCT #8130)

USE: An oil-based asphalt pavement sealer designed to fill hairline cracks, beautify asphalt surfaces and rejuvenated dried-out asphalt surfaces (Contains Gilsonite). Does not contain water.

PRODUCT DESCRIPTION: An oil-based driveway sealer that penetrates and rejuvenates dried out asphalt surfaces and seals hairline cracks. Provides a black protective finish, which helps eliminate water penetration and prevent freeze/thaw cracking. Dries to a rich glossy black finish while protecting the pavement binder from oxidation damage.

PREPARATION: The surface should be clean and dry. Oil and grease spots should be scrubbed with driveway cleaner, strong household or dishwashing detergent. Flush the area with clean water and allow to dry before sealing. Cracks wider than hairline should be filled with asphalt crackfiller or blacktop patch. Allow filled cracks to dry prior to sealing.

APPLICATION: Apply coating with brush, squeegee or medium nap roller. Spread evenly, working sealer into driveway pores. Apply coating as thin as possible and do not allow puddling in low areas. Final brush strokes should be in one direction for best results. Clean up with Mineral Spirits.

COVERAGE: Unsealed driveways – 75 sq.ft./gallon; Previously sealed – 100 sq.ft./gal. Recommended coverage rates should be followed as close as possible. Over application may cause surface to become slippery.

DRY TIME: Under normal conditions the sealer will dry to the touch in 1-2 hours and may be opened to traffic in 24 hours. Application at higher than recommended coverage rates can dramatically increase drying times.

FOR BEST RESULTS:

#81300 Asphaltic Driveway Sealer

- * Do **NOT** use on driveways less than 1 year old.
- * Do **NOT** apply on driveways previously sealed with Coal Tar Emulsion. *Best results are achieved when applied at temperatures below 80°F. Hot and humid days can cause the top surface of the sealer to prematurely dry. This may lead to re-emulsification and browning. In the case of browning, gently wash the surface with a solution of T.S.P. (Tri Sodium Phosphate) and water. Then rinse the driveway with clean tap water. If the sealer must be applied on extremely hot days, plan your work to begin early in the morning or evening when the driveway temperature is lower.

PACKAGING: 55-gallon drums and 5-gallon pails

SHIPPING WEIGHT: 55 Gallon = 460#, 5 Gallon = 42#

SPECIFICATIONS:

Flash Point.....	105 F min.
Weight per gallon.....	7.4 lbs.
Non-volatile.....	60% min.
% of specially compounded.....	58% min.
bitumen	
% of total solids by volume.....	64% min.
Film thickness.....	4-5 mils
Drying time.....	12-24 hours
Resistance to oils & solvents.....	Poor
Resistance to chemicals.....	Good

Resistance to Sunlight.....	Good
Effect of weathering.....	Slow Erosion
Water resistance under good.....	Excellent
drainage conditions	
Water resistance under.....	Fair
Continuous submersion	

CAUTION: Combustible. Keep away from open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after use. Use with adequate ventilation. Do not take internally. In the case of ingestion or eye contact, contact physician immediately.

KEEP OUT OF REACH OF CHILDREN