

•634 Route 228 • P.O. Box 599 • Mars, PA. 16046 • 724-625-3116 • FAX 724-625-1640

•4111 Walden Ave • Lancaster, NY 14086 • 716-681-1581 • FAX 716-681-1513

•900 W. Smith Rd. • Medina, OH 44256 • 330-723-7780 • FAX 330-723-7780







ASPHALT EMULSION FOUNDATION COATING

(Product #82900, 1/03/01)

Product Description: An asphalt base, clay stabilized emulsion that produces a tight,

tack free film. This coating provides excellent protection and resistance to water. The applied film is a so-called "breather" type which permits water vapor to escape while remaining resistant to water. This characteristic helps prevent blistering and recommends its use in all areas subject to severe moisture conditions. Asphalt Emulsion Foundation Coating reduces VOC emissions by using water as a coating vehicle instead of solvents. Product may be cleaned with soap and water prior to drying. Dried product may be cleaned with mineral spirits.

<u>Uses:</u> - Recommended for damproofing above & below grade masonry surfaces.

- May be used as a vapor retarder against dampness on exterior walls.
- May be used as an adhesive for polystyrene insulation or protection board.

<u>Surface Preparation</u>: Surface to be coated must be cleaned thoroughly of all loose mortar, oil, grease, dust and debris. This coating may be applied over damp surfaces, however, excess or ponding water should be removed.

<u>Application:</u> Stir coating to reincorporate any separated vehicle. If the product appears too thick, it may be thinned using water. Apply coating by brush, roller or spray. Coating may appear brown in container but will dry to a rich black surface.

Coverage: Will vary depending on age, dryness and porosity of surface.

Approximate rate: $2 - 2\frac{1}{2}$ gallons per 100 sq. ft. = concrete and masonry surface.

 $1 \frac{1}{2} - 2$ gallons per 100 sq. ft. = metal

Product Specifications: ASTM D-1227, SS-R-1781, MIL-R-3472A

Color and Texture Smooth, black finish

Product Type Clay Stabilized Asphalt Emulsion

Filler Non-Asbestos

Specific Gravity 1.04

Flash Point, C.O.C. Not applicable

Sprayability Down to 32°F., recommend 15:1 Ratio Airless

Pump - .024-.030 Tip Size

CAUTION: DO NOT FREEZE!!!!

Avoid repeated or prolonged contact with skin. Avoid contact with eyes. If swallowed, <u>DO NOT</u> induce vomiting. Contact physician immediately.

KEEP OUT OF REACH OF CHILDREN