FBC CHEMICAL CORP.

●634 Route 228 • P.O. Box 599 • Mars, PA. 16046 • 724-625-3116 • FAX 724-625-1640
●4111 Walden Ave • Lancaster, NY 14086 • 716-681-1581 • FAX 716-681-1513
●900 W. Smith Rd. • Medina, OH 44256 • 330-723-7780 • FAX 330-723-7780
●7301 Bessemer Avenue • Cleveland, OH 44127 • 216-341-2000 • FAX 216-341-5833



ASPHALT FOUNDATION TROWEL-ON MASTIC

(PRODUCT #82650)

USE: For waterproofing outside cement block, concrete or brick foundations.

PRODUCT DESCRIPTION: A trowel grade, heavy bodied protective coating made with an asphalt base.

APPLICATION: Use stiff brush or broom to remove dust, dirt and debris. Allow green concrete to cure thoroughly. Apply with trowel at rate of 4 gallons per 100 square feet.

CAUTION: Allow mastic to thoroughly dry 2-3 days; then when back filling, be Careful to prevent sharp rocks, stones, etc. from piercing coating.

SPECIFICATIONS: Meets Performance Requirements of Federal Specification SS-C-153C, Type 1. Meets ASTM D 4586 (Type 1).

Color……. Black – Dark Brown
Total Solids Content…… 72%
Solvent Content…… 28%
Solvent Type…… Mineral Spirits, Rule 66 or Equiv.
Flash Point (T.C.C.)…….. 105 F
Weight per gallon @ 60 F……. 9-9.5#
Base Asphalt
Softening Point (B&R)……. 125-145F
Penetration 77 F
5 sec., 100 grs…… 30-60

PACKAGING: 55-gallon drums and 5-gallon pails

SHIPPING WEIGHTS: 55 gallons = 465#, 5 Gallons = 43#