

•634 Route 228 • P.O. Box 599 • Mars, PA. 16046 • 724-625-3116 • FAX 724-625-1640 •4111 Walden Ave • Lancaster, NY 14086 • 716-681-1581 • FAX 716-681-1513 •900 W. Smith Rd. • Medina, OH 44256 • 330-723-7780 • FAX 330-723-7780 •7301 Bessemer Avenue • Cleveland, OH 44127 • 216-341-2000 • FAX 216-341-5833





## **MODIFIED BITUMEN ADHESIVE (Brush or Trowel Grade)**

## (PRODUCT #82820)

**PRODUCT DESCRIPTION:** A rubberized asphalt-based adhesive fortified with SBS polymers and fibers. This product is specifically designed for cementing polymer modified asphalt coated membranes together. It sets by loss of solvent through evaporation producing a strong bond with excellent low temperature flexibility. The cured bond resists failures associated with thermal shock and eliminates many of the fire hazards associated with torch or hotmopped systems. Also may be used as a professional grade cold-lap cement.

- **SURFACE PREPARATION:** Surface must be dry, clean and free of oil, dust, dirt, loose aggregate and other debris. Heavily weathered or exposed felt surfaces as well as concrete, masonry or rusted metal may require priming.
- **APPLICATION:** Apply Modified Bitumen Adhesive with a squeege, brush or serrated trowel at a rate of 1-2 gallons per 100 square feet depending on surface irregularities. Overlap edges a minimum of 4 inches and end laps 6 inches. No dwell time is required prior to embedding or overlapping membrane.

**COVERAGE:** Will vary depending upon age, dryness and porosity of surface. Approximate rates:

Brush Grade: 1-2 gallons per 100 square feet Trowel Grade: 2 gallons per 100 square feet

**CLEAN-UP:** Equipment and brushes may be cleaned using Mineral Spirits or Kerosene. Care should be taken when handling these solvents. Use waterless hand cleaner on skin.

**CAUTION:** COMBUSTIBLE. Contains petroleum distillates. Keep away from heat, sparks and open flame. Use only with adequate ventilation. If you experience eye watering, headaches or dizziness increase fresh air, wear respiratory protection (NIOSH/MSHA TC23C) or leave area.

\*\* Not recommended for use with APP Modified Roofing or torch applied systems with Polyethylene backing.